

BUNA SL 7518-4

Product Description

Buna® SL 7518-4 is oil extended copolymer of butadiene and styrene containing 18% of bounded styrene. It is produced by solution polymerization process using an alkyl-lithium initiator. The low vinyl content provides a low Tg which gives an excellent low temperature flexibility, abrasion

resistance and low rolling resistance. Corresponding vulcanizates of this product have superior resistance to reversion. The polymer is stabilized with non-staining antioxidants.

Buna® SL 7518-4 has excellent properties in the manufacture of tires, retreads, moulded technical parts, injected or extruded goods, surgical goods, shoe soles and automotive industry parts. In tire manufacture it is blended with NR, BR or E-SBR.

Supply Form

Bales

Polymer Properties

Property	Nominal Value with Unit	Test Method
Mooney Viscosity ML (1+4) 100 °C	75 MU	ISO 289 / ASTM D 1646
Styrene Content	18 wt %	Internal Method
Oil Content	13 wt %	ASTM D 5774

Other Product Features

Property	Typical Value with Unit	Test Method
Density	0,91 g/cm ³	ASTM D 297
Packaging	31 kg bales wrapped in PE film; 36 bales in a box (1116 kg)	
Storage Conditions	The product should be stored dry and at temperature < 35°C. Exposure to light has to be avoided.	
Product Safety	Literature on the health and safety aspects of this product has been published. Before working with this product, personnel must be familiarised with its hazards, proper use, and handling. The available information is summarised in the Safety Data Sheet.	

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.



Buna® is a trademark of ARLANXEO Deutschland GmbH

Disclaimer

"ARLANXEO makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document (the "Information") about its accuracy, suitability for particular applications, or the results obtained or obtainable using the Information. Some of the Information arises from laboratory work with small-scale equipment that may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. ARLANXEO makes no warranties, express or implied, including, but not limited to, implied warranties of merchantability and fitness for a particular purpose, with respect to the Information, ARLANXEO's products listed in the Information, or the suitability of either ARLANXEO's products, or the Information, for your process or end-use application. This document and the Information shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any offer to sell, offer to purchase, or sale of ARLANXEO's products are expressly governed by ARLANXEO's general terms and conditions of sale applicable to the ARLANXEO legal entity selling, or offering to sell, any such product."



GLOBUS RUBCHEM (P) LTD.

Kolkata | Mumbai | Chennai | Bangalore

Date of Release: 01.02.2021 / Information current as of date of issue. Please contact your ARLANXEO representative to determine if this publication has been revised.