

ESBR : Emulsion Styrene Butadiene Rubber

Solution*Partner*

● Grades Information

Product	Polymer					Application
	Appearance	Mooney Viscosity	Extended oil	Oil (phr)	Styrene (%)	
1500	Dark brown	52	-	-	23.5	Tire, Belt, Industrial goods
1502	Light tan	52	-	-	23.5	Tire, Belt, Shoe-sole, Industrial goods
1521	Light tan	45	-	-	21.0	Tire

● Shelf life / Condition

- It should be stored in warehouse to be protected from sunlight, heat and moisture.
- Shelf life : 24 months from date of production at room temperature not exceeding 30°C under above storage condition.
(Retest critical parameters like MV and others after the expiry of shelf life)