

# ESBR : Emulsion Styrene Butadiene Rubber

**SolutionPartner**

## ● Grades Information

Product	Polymer					Application
	Appearance	Mooney Viscosity	Extended oil	Oil (phr)	Styrene (%)	
1712	Dark brown	49	DAE	37.5	23.5	Tire, Belt, Industrial goods
1723	Dark brown	44	TDAE	37.5	23.5	Tire, Belt
1723H	Dark brown	49	TDAE	37.5	23.5	Tire, Belt
1737	Dark brown	52	TDAE	34.0	37.0	Tire, Belt
1739	Dark brown	53	TDAE	37.5	40.0	Tire, Belt
1778	Light tan	46	Naphthenic	37.5	23.5	Tire, Shoe-Sole, Belt
1783	Dark brown	49	RAE	37.5	23.5	Tire, Belt
1789	Dark brown	54	RAE	37.5	40.0	Tire, Belt

## ● Shelf life / Condition

- It should be stored in warehouse to be protected from sunlight, heat and moisture.
- Shelf life : 24 months from date of production at room temperature not exceeding 30°C under above storage condition.  
(Retest critical parameters like MV and others after the expiry of shelf life)