

ESBR : Emulsion Styrene Butadiene Rubber

SolutionPartner

● Grades Information

| Product | Polymer | | | | | Application |
|---------|------------|------------------|--------------|-----------|-------------|------------------------------|
| | Appearance | Mooney Viscosity | Extended oil | Oil (phr) | Styrene (%) | |
| 1712 | Dark brown | 49 | DAE | 37.5 | 23.5 | Tire, Belt, Industrial goods |
| 1723 | Dark brown | 44 | TDAE | 37.5 | 23.5 | Tire, Belt |
| 1723H | Dark brown | 49 | TDAE | 37.5 | 23.5 | Tire, Belt |
| 1737 | Dark brown | 52 | TDAE | 34.0 | 37.0 | Tire, Belt |
| 1739 | Dark brown | 53 | TDAE | 37.5 | 40.0 | Tire, Belt |
| 1778 | Light tan | 46 | Naphthenic | 37.5 | 23.5 | Tire, Shoe-Sole, Belt |
| 1783 | Dark brown | 49 | RAE | 37.5 | 23.5 | Tire, Belt |
| 1789 | Dark brown | 54 | RAE | 37.5 | 40.0 | Tire, Belt |

● Shelf life / Condition

- It should be stored in warehouse to be protected from sunlight, heat and moisture.
- Shelf life : 24 months from date of production at room temperature not exceeding 30°C under above storage condition.
(Retest critical parameters like MV and others after the expiry of shelf life)