



Lion Copolymer Geismar, LLC

36191 Highway 30 • Geismar, LA 70734
800 / 535-9960 • www.lionelastomers.com

Royalene[®] 525 EPDM

Product Data

" An Ultra Fast Curing Polymer for Automotive Extrusions "

Unique Features

- ▶ High unsaturation - Ultra fast cure rate
- ▶ Excellent compression set resistance in closed cell sponge extrusions
- ▶ Excellent low temperature properties
- ▶ Co-cures well with SBR
- ▶ Non-staining
- ▶ Friable bale form for rapid mixing in internal mixers and excellent dispersion properties
- ▶ Excellent weathering resistance

Applications

- ▶ Closed cell sponge profile extrusions
- ▶ Closed cell sheet sponge
- ▶ Automotive window channel extrusions

Raw Polymer Properties

	Test Method*	Typical
Mooney Viscosity, ML (1+4)/125°C (Unmilled)	ZS 1220B	65
E/P Weight Ratio	ZS 1231	60/40
ENB, Weight %	ZS 1222	8.1
Molecular Weight Distribution	ZS 1296A	Medium
Volatile Matter, Weight %	ZS 1008K	0.7 Max.
Stabilizer	—	Non-Staining
Specific Gravity, g/cc	ASTM D-792	0.86
Color	ZS 1072A	Light Amber
Physical Form, lbs/bale	—	55.1 (25 kg) (Friable bale)

* Company Test Methods
Royalene 525

HWY 5/18

Notice: All information supplied by or on behalf of Lion Copolymer Geismar, LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Copolymer Geismar, LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Copolymer Geismar, LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.