

# SSBR : Solution Styrene Butadiene Rubber

**SolutionPartner**

## ● Grades Information

Product	Polymer						Properties(Application)
	Styrene (%)	Vinyl <sup>1)</sup> (%)	Extended oil	Oil (phr)	Mooney Viscosity	Tg (°C)	
2550	25	50	TDAE	37.5	50	-28	Performance, High performance tire
2550H	25	50	TDAE	37.5	62	-28	Performance, High performance tire
3323	33	23	TDAE	37.5	60	-40	Good abrasion, High performance tire
3626	36	26	TDAE	37.5	53	-34	Well balanced of LRR and Grip
3824	38	24	TDAE	37.5	82	-32	Good Wet Grip Block styrene exist

1) Vinyl on Polymer

## ● Shelf life / Condition

- It should be stored in warehouse to be protected from sunlight, heat and moisture.
- Shelf life : 24 months from date of production at room temperature not exceeding 30°C under above storage condition.  
(Retest critical parameters like MV and others after the expiry of shelf life)