



NORDEL™ IP 3640

Hydrocarbon Rubber

Overview

NORDEL™ IP 3640 Hydrocarbon Rubber is an amorphous and low diene-containing ethylene-propylene-diene terpolymer (EPDM) and is suitable for heat resistant peroxide cured moldings. NORDEL IP 3640 can be blended with butyl rubber to improve processing and vulcanizate properties of automotive and bicycle tire innertubes.

Main Characteristics:

- Amorphous
- Low diene
- Good heat resistance

- Complies with

U.S. FDA 21 CFR 177.2600,
 U.S. FDA 21 CFR 177.1520 (See NOTES 1),
 U.S. FDA 21 CFR 175.105 (See NOTES 2),
 U.S. FDA 21 CFR 177.1210.
 Consult the regulations for complete details.

Applications:

- Blend component with butyl rubber in innertubes
- Heat resistant hoses and belts

NOTES:

- (1) Can be used in contact with all foods except water in oil emulsions, high or low fat, and low moisture fats and oil.
 (2) Adhesives only.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.860 g/cm ³	0.860 g/cm ³	ASTM D297
Ethylene Content	55.0 wt%	55.0 wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	1.8 wt%	1.8 wt%	ASTM D6047
Mooney Viscosity (ML 1+4, 257°F (125°C))	40 MU	40 MU	ASTM D1646
Ash Content	< 0.10 %	< 0.10 %	ASTM D5667
Molecular Weight Distribution	Medium	Medium	Dow Method
Propylene Content	43.2 wt%	43.2 wt%	ASTM D3900
Residual Transition Metal	< 10 ppm	< 10 ppm	Dow Method
Volatile Matter	< 0.40 wt%	< 0.40 wt%	Dow Method

Additional Information

Storage and Handling:

The quality of EPDM products may be affected by exposure to artificial or natural light. This product should be stored indoors in its original packaging and out of direct sunlight.

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

Additional Information

North America		Europe/Middle East	+800-3694-6367
U.S. & Canada:	1-800-441-4369		+31-11567-2626
	1-989-832-1426	Italy:	+800-783-825
Mexico:	+1-800-441-4369		
Latin America		South Africa	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	Asia Pacific	+800-7776-7776
Mexico:	+52-55-5201-4700		+603-7965-5392

www.dowplastics.com

This document is intended for use within Asia Pacific, Europe, Latin America, North America

Published: 2005-05-05

© 2019 The Dow Chemical Company

